

LIMESTONE



Limestone is used mainly in the iron making part of steel production where it is added to the iron ore before entering the blast furnace. The limestone reacts with acidic impurities called slag and floats on top of the molten iron where it is skimmed off.

Aegis provides large scale of sizes which can be used by steel, cement, or glass manufacturers.

ORIGIN



SPECIFICATIONS

SPECIFICATIONS OF LIMESTONE UAE

S.N.	Parameters	Typical Specifications
1.	CaO	54.00% Min
2.	MgO	1.50% Max
3.	SiO ₂	0.60% Max
4.	Fe ₂ O ₃	0.20% Max
5.	LOI	43.00% Min
6.	Alkali	0.20% Max
7.	Al ₂ O ₃	0.30% Max
8.	S	0.025% Max
9.	Water Absorption	2.00% Max
10.	P	0.025% Max
11.	Moisture	0.50% Max

SPECIFICATIONS OF LIMESTONE OMAN

S.N.	Parameters	Typical Specifications
1.	CaO	54.00% Min
2.	MgO	1.50% Max
3.	SiO ₂	0.55% Max
4.	Fe ₂ O ₃	0.20% Max
5.	Na ₂ O + K ₂ O	0.15% Min
6.	Al ₂ O ₃	0.30% Max

AEGIS CARRIERS DMCC

3301, JBC-1, Cluster-G
Jumeirah Lakes Towers
PO Box: 487606,
Dubai, UAE.

Tel: +971- 4 5546936
Fax: +971- 4 5546935

For General information
info@aegiscarriers.com

For Chartering team
dry@aegiscarriers.com

For Operation team
ops@aegiscarriers.com

AEGIS RESOURCES DMCC

3708, JBC-1, Cluster-G
Jumeirah Lakes Towers
PO Box: 336906
Dubai, UAE.

Tel: +971- 4 5546936
Fax: +971- 4 5546935

For General information
admin@aegis-overseas.com

For International Sales
sales@aegis-overseas.com